

SHAPED PRODUCT	MULL-65
-----------------------	----------------

CLASSIFICATION UNE EN ISO 10081 UNE-EN 12475-4	Dense firebrick, ceramic bonded. Base andalusite. Group HA 55
---	---

REFERENCE	932156	0513	491.RC	GROUP	FAMILY	STANDARD
				LD	30	

CHEMICAL AVERAGE ANALYSIS (Obs "A")

Al₂O₃	63,0	%
SiO₂	34,0	%
Fe₂O₃	1,2	%
CaO	0,3	%

PHYSICAL PROPERTIES

Classification Temperature	1560	°C	
Aparent density (dense material)	2,50	Kg./dm ³	EN 993-1
Open porosity (dense material)	14,0	%	EN 993-1
Cold crushing strength:			
Dense material	500	Kg./cm ²	EN 993-5
Softening under load	1560	°C	EN ISO 1893
Sudden change in temperature	25	Cycles	PRE / R.5.1
Linear reversible dilation	1000 °C	0,60	%
Thermal conductivity	400 °C	1,20	W/m.K
	800 °C	1,40	W/m.K
	1200 °C	1,70	W/m.K

OBSERVATIONS

Old A-160

"A" Alternative method= Spectrometry by FRX

Applicable standards indicated. Other standards prior arrangements.

The thecnical characteristics represent the medium values from reconized essay methods of standard materials; they are under the normal variations ofmanufacturins and should not be considered like specifications.

EQUIVALENCES

1 N/mm² = 1 MPa = 10,2 kg/cm²

1 kg/cm² = 0,098 MPa = 0,098 N/mm²

1 W/mK = 0,86 kcal/mhK

1 Kcal/mK = 1,16 W/mK