

<b>SHAPED PRODUCT</b>	<b>R-COR-SCO-5</b>
-----------------------	--------------------

<b>CLASSIFICATION</b> UNE EN ISO 10081 UNE-EN 12475-4	Dense refractory support piece of ceramic bounded. Base calcined refractory clay and cordierite. Group FC 30
---	--

REFERENCE	937674	0320	707.RC	GROUP	FAMILY	STANDARD
				DE	10	

**CHEMICAL AVERAGE ANALYSIS (Obs "A")**

<b>Al<sub>2</sub>O<sub>3</sub></b>	31,0	%
<b>SiO<sub>2</sub></b>	59,0	%
<b>Fe<sub>2</sub>O<sub>3</sub></b>	2,6	%
<b>MgO</b>	4,8	%

**PHYSICAL PROPERTIES**

<b>Classification Temperature</b>	1200		°C	
<b>Apparent density (dense material)</b>	2,00		Kg./dm <sup>3</sup>	EN 993-1
<b>Open porosity (dense material)</b>	18,0		%	EN 993-1
<b>Cold crushing strength:</b>				
<b>Dense material</b>	200		Kg./cm <sup>2</sup>	EN 993-5
<b>Sudden change in temperature</b>	<b>WATER</b>	>	90	Cycles PRE / R.5.1
<b>Linear reversible dilation</b>	<b>1000 °C</b>	0,35	%	
<b>Thermal conductivity</b>	<b>400 °C</b>	0,95	W/m.K	
	<b>800 °C</b>	1,10	W/m.K	
	<b>1200 °C</b>	1,35	W/m.K	

"A" Alternative method= Spectrometry by FRX

Applicable standards indicated. Other standards prior arrangements.

The technical characteristics represent the medium values from recognized essay methods of standard materials; they are under the normal variations of manufacturers and should not be considered like specifications.

**EQUIVALENCES**

1 N/mm<sup>2</sup> = 1 MPa = 10,2 kg/cm<sup>2</sup>  
 1 kg/cm<sup>2</sup> = 0,098 MPa = 0,098 N/mm<sup>2</sup>  
 1 W/mK = 0,86 kcal/mhK  
 1 Kcal/mK = 1,16 W/mK