

PRODUCT NOT CONFORMED**LIQUIDO ADHESIVO****CLASIFICACION**
ISO 1927-1**REFERENCE**

0513

12.RT

GROUP**FAMILY**

STANDARD

NC

90

AVERAGE CHEMICAL ANALYSIS (Obs "A")

SiO ₂	26,0	%
Na ₂ O	8,0	%

PHYSICAL PROPERTIES

Classification temperature	1000	°C	ISO 1927-1
Bulk density	Dry 110°C	1,35	Kg./dm ³ ISO 1927-6

OBSERVATIONS

Refractory adhesive liquid to glue insulation materials, ceramic fiber blanket, silicate boards, ceramic paper, etc.
 Dry extract 34%
 Expiration.- Unlimited in tightly closed container

"A" alternative Method = Spectrometry by FRX

The technical characteristics represent the obtained average values according to methods of tests recognized on standardized materials; they are put under the normal variations of manufacture and they do not have to be taken like specifications. The data of density and compressive strenght will not be valid for manual productions.

EQUIVALENCES

1 N/mm² = 1 MPa = 10,2 kg/cm²
 1 kg/cm² = 0,098 MPa = 0,098 N/mm²
 1 W/mK = 0,86 kcal/mhK
 1 Kcal/mK = 1,16 W/mK